

POLYMEX-3000-Poliüretan Halı Saha Yapıştırıcısı **P-3000-Poliüretan Halı Saha Yapıştırıcısı**

Ürün Tanımı

İki bileşenli, solvent ihtiva etmeyen, poliüretan esaslı çok maksatlı halı saha yapıştırıcısıdır. Halı Saha zemin kaplama sistemlerinde yapıştırıcı olarak kullanılır. Poliüretan Halı Saha Yapıştırıcısı Poliüretan Halı Saha Yapıştırıcısı



Kullanıldığı Yerler

Poliüretan Halı Saha Yapıştırıcısı Kauçuk kaplamalarının, seramik, granitlerin yere yapıştırılmasında; kauçuk kaplamalarının oyun ve diğer zemine ve duvarlara yapıştırılmasında kullanılan güçlü bir poliüretan yapıştırıcıdır. Her cins Kauçuğun ve parkenin yapıştırılmasında kullanılır. Polymex P-3015; ahşabı betona yapıştırmada diğer cins yapıştırıcılara göre çok daha iyi sonuçlar verir. Isıya dayanıklı bir poliüretan olmasından dolayı alttan ısıtmalı sistemlerde kullanılabilir. Gün ışığı ve sudan etkilenmemesinden dolayı yapıştırma özelliği 20 yıla kadar sürer. Beyaz eşya sektöründe üst tablo imalinde plastik akşamların suntaya yapıştırılmasında çok maksatlı olarak değişik sektörlerde de kullanılmaktadır. Saplı sapsız zımparalarda plastik ile zımpara kâğıtlarının yapıştırılmasında kullanılmaktadır. Polietilen ve benzerleri hariç. Beton, taş, ahşap. Metal, aternit gibi her türlü yüzeye tatbik edilir. Kimyasallara, darbelere ve sürtünmeye dayanıklı sıvı sızdırmayan anti bakteriyel yapıştırıcıdır. Uygulandığı zeminde düzgün yüzey oluşturur ve yüzey mukavemetini artırır ve güçlendirir. Poliüretan Halı Saha Yapıştırıcısı.

Özellikler

Su, rutubet, darbe, asit-baz, deniz suyu, çoğu kimyasal ve korrozif malzemelere karşı dayanıklıdır. Sertleşme sonrasında gayet sağlam bir tabaka meydana getirir.

Uygulandığı yüzeye aderansı yüksek bir poliüretan malzemedir. Uygulanan yüzeyin uzama ve elastikiyet katsayılarını aşar. Poliüretan Halı Saha Yapıştırıcısı.

Uygulama

Poliüretan Halı Saha Yapıştırıcısı:Önce büyük kovadaki malzeme (A Bileşeni) matkap ile iyice karıştırılır. Sonra küçük kutudaki sertleştirici (B komponenti) büyük kovadaki ana malzemeye 5'e 1 oranında dökülür homojen bir karışım sağlanıncaya kadar mikser ile düşük devirde karıştırılır. Hazırlanan karışım 45 dakika ile 55 dakika arasında kullanılmalıdır. Mala, Rulo veya tarak ile uygulayın. Sathı bozuk ve nemli yüzeylerde uygulama öncesi Polymex çift komponentli şeffaf astar uygulayın.

AŞY POLYMEKS KİMYA SAN TİC LTD ŞTİ

Head Office:Alemdağ cad İhlamur kuyu Mah Hürmet Sok No:4 Ümraniye / İSTANBUL
Tel:+90 216 540 67 03 -04 Fax :+90 216 365 47 15

www.polymex.com.tr

POLYMEX P-3000

Tatbik edilecek yüzey zemin düzgün. Kuru. Ve temiz olmalıdır. Madeni yağ kir pas ve çapaklardan arındırılmalıdır. Kesinlikle yabancı malzeme ilave edilmemelidir. Uygulamada ortam ve yüzey sıcaklığı +10 °C 'nin altında yada +30 °C nin üzerinde ise uygun sıcaklıklar beklenmelidir. Uygulamada kullanılan makine ve aparatları, kullanım sonrasında uygun temizleyici ile temizleyin. Poliüretan Halı Saha Yapıştırıcısı.

Depolama ve Raf Ömrü:

Açılmamış orijinal ambalajında standart oda koşullarında 24 ay saklanabilir.

Sarfiyat:

Yaklaşık olarak m² de 1 kg uygulanır. Sarfiyat zeminin emiciliğine bağlı olarak değişebilir.

Ambalaj:

10.kg, 24,kg 30 ve 36 Kg'lık setler halindedir.

Teknik Özellikler:

Renk	Krem, Kırmızı, Gri.(İstenilen Renk) Genellikle krem kullanılır.
Sertlik Shore A	75 – 80
Bağlayıcı Madde	Poliüretan Reçine
Yoğunluk	A Bileşeni: 1,40 gr/ml B Bileşeni: 1,22 gr/ml
Karışım Oranı	5/1 kg ağırlıkça
Uygulama süreci(23 °C)	50 ile 60 Dakika Arası
Katılma Başlangıcı	25 °C /+40 °C sıcaklıklarında 45 dakika
Sıcaklığa Dayanım	-40/ +280 °C
Kürünü Tamamlama (20C)	12 saat sonra kürünü tamamlama (tam kuruma 48 saat)
Kauçuk Yapıştırıcısı Çevreye uyum	Çevreye olumsuz etkisi yok
Kürünü Tamamlama(20 °C ve%60 relatif nem)	Kuruma süresi dolmadan parkelerin yerleştirilmesi gerekir. Bir gün sonra üzerlerinde gezilebilir ve cila yapılabilir.
Gerilme mukavemeti	30 Kg/cm ² (DIN 53455)
UV ışınları ve Malzeme sıcaklığı	Dayanıklısıdır

Uyarılar:

Sertleştiricinin cilde temasından kaçınılmalıdır. Yutulması durumunda midenin yıkanıp yıkanmamasına karar verebilecek bir doktora başvurulmalıdır. Koruyucu gözlük ve eldiven giyilmesi tavsiye edilir.

Notlar:

Bu ürün bilgi föyünde bulunan tüm teknik veriler laboratuvar deneylerine dayanmaktadır. Gerçek de elde edilen veriler, AŞY POLYMEKS KİMYA SAN TİC LTD ŞTİ. 'nin kontrolünün ötesindeki şartlar sebebiyle değişkenlik gösterebilir.

POLYMEX-3000-Poliüretan Halı Saha Yapıştırıcısı

AŞY POLYMEKS KİMYA SAN TİC LTD ŞTİ

Head Office:Alemdağ cad İhlamur kuyu Mah Hürmet Sok No:4 Ümraniye / İSTANBUL
Tel:+90 216 540 67 03 -04 Fax :+90 216 365 47 15

POLYMEX-3000-Polyurethane Carpet Adhesive Polyurethane Carpet Adhesive

Product description

It is a two-component, solvent-free, polyurethane-based multi-purpose carpet field adhesive. It is used as an adhesive in Carpet Field floor covering systems. Polyurethane Carpet Adhesive Polyurethane Carpet Adhesive

Where Used

Polyurethane Carpet Adhesive For bonding rubber coatings, ceramics, granites to the ground; It is a strong polyurethane adhesive used for bonding rubber coatings to playgrounds and other floors and walls. It is used for bonding all kinds of rubber and parquet. Polymex P-3015; It gives much better results in bonding wood to concrete than other types of adhesives. Since it is a heat resistant polyurethane, it can be used in systems with underfloor heating. Since it is not affected by sunlight and water, its bonding feature lasts up to 20 years. It is also used in different sectors for multi-purposes in the production of upper tables in the white goods sector, in bonding plastic evenings to chipboard. It is used for bonding plastic and sandpaper in handleless and handleless sanders. Except for polyethylene and the like. Concrete, stone, wood. It is applied to all kinds of surfaces such as metal, aternite. It is a liquid-proof, anti-bacterial adhesive that is resistant to chemicals, impacts and friction. It creates a smooth surface on the floor where it is applied and increases and strengthens the surface strength.



Features ,

It is resistant to water, humidity, impact, acid-base, sea water, most chemicals and corrosive materials. It creates a very solid layer after hardening. It is a polyurethane material with high adherence to the applied surface. It exceeds the elongation and elasticity coefficients of the applied surface.

APPLICATION

Polyurethane Carpet Adhesive: First, the material in the big bucket (Component A) is mixed thoroughly with a drill. Then, the hardener (component B) in the small box is poured into the main material in the big bucket at a ratio of 5 to 1 and mixed with a mixer at low speed until a homogeneous mixture is obtained. The prepared mixture should be used between 45 minutes and 55 minutes. Apply with a trowel, roller or comb. Apply Polymex two-component transparent primer before application on uneven and damp surfaces.

The surface to be applied is smooth. Dry. And it should be clean. Mineral oil should be cleaned of dirt, rust and burrs. Absolutely no foreign material should be added. If the ambient and surface temperature is below +10 oC or above +30 oC in the application, suitable temperatures should be expected. Clean the machines and apparatus used in the application with an appropriate cleaner after use.

AŞY POLYMEKS KİMYA SAN TİC LTD ŞTİ

Head Office:Alemdağ cad İhlamur kuyu Mah Hürmet Sok No:4 Ümraniye / İSTANBUL
Tel:+90 216 540 67 03 -04 Fax :+90 216 365 47 15

Storage and Shelf Life:

It can be stored for 24 months under standard room conditions in its unopened original package.

Consumption:

Approximately 1 kg is applied per m2. Consumption may vary depending on the absorbency of the floor.

PACKAGING:

It is in sets of 10.kg, 24.kg, 30 and 36 kg.

Technical Specifications:

Color Cream, Red, Grey. (Desired Color) Usually cream is used.

Hardness Shore A 75 – 80

Binder Polyurethane Resin

Density Component A: 1.40 gr/ml Component B: 1.22 gr/ml

Mixing Ratio 5/1 kg by weight

Application period (23 oC) Between 50 and 60 Minutes

Onset of Solidification 45 minutes at 25 oC / +40 OC

Temperature Resistance -40/ +280 oC

Completion of Curing (20C) Completion of curing after 12 hours (full drying 48 hours)

Rubber Adhesive Environmental Compliance No negative impact on the environment

Completing its Curing (20 oC and 60% relative humidity) The parquets must be placed before the drying time expires.

After a day, they can be walked on and polished.

Tensile strength 30 Kg/cm2 (DIN 53455)

Resistant to UV rays and Material temperature

Warnings:

Skin contact of the hardener should be avoided. In case of swallowing, a doctor should be consulted who can decide whether or not to wash the stomach. It is recommended to wear safety glasses and gloves.

Notes:

All technical data contained in this product data sheet are based on laboratory tests. In fact, the data obtained, AŞY POLYMEKS KİMYA SAN TİC LTD ŞTİ. may vary due to circumstances beyond our control.

POLYMEX-3000-Polyurethane Carpet Adhesive

AŞY POLYMEKS KİMYA SAN TİC LTD ŞTİ

Head Office:Alemdağ cad İhlamur kuyu Mah Hürmet Sok No:4 Ümraniye / İSTANBUL
Tel:+90 216 540 67 03 -04 Fax :+90 216 365 47 15